

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Currently Amended) A granular substance ~~characterized by comprising~~
consisting of:
 ~~a matrix composed of a~~ nonmagnetic insulating organic material; and
 ferromagnetic metal particles dispersed in said ~~matrix~~ nonmagnetic insulating
 organic material and having a mean particle size of 50 nm or less,
 wherein the volume ratio of said ~~matrix~~ nonmagnetic insulating organic material
in said granular substance is in the range of 5 to 50%.
2. (Original) The granular substance according to claim 1, characterized in that
said ferromagnetic metal particles are formed of a metal mainly comprising at least one
element selected from Fe, Co and Ni.
3. (Original) The granular substance according to claim 1, characterized in that
said ferromagnetic metal particles are formed of a metal mainly comprising Fe and Co.
4. (Original) The granular substance according to claim 3, characterized in that
the concentration of Co in said metal mainly comprising Fe and Co is in the range of 10
to 50 at%.
5. (Original) The granular substance according to claim 1, characterized in that
said ferromagnetic metal particles are spaced apart by a distance enabling exchange
coupling therebetween.

6. (Currently Amended) The granular substance according to claim 1, characterized in that said ~~matrix~~ nonmagnetic insulating organic material is formed of an organic polymer.

7. (Currently Amended) The granular substance according to claim 1, characterized in that the volume ratio of said ~~matrix~~ nonmagnetic insulating organic material is in the range of 5 to 40%.

8. (Original) The granular substance according to claim 1, characterized in that said granular substance is in the form of a film, and has a complex permeability the real part (μ') of which is 40 or more at 1 GHz, a quality factor Q ($Q = \mu' / \mu''$ where μ'' is the imaginary part of the complex permeability) of 1 or more, and a saturation magnetization of 5 kG or more.

9. (Original) The granular substance according to claim 8, characterized in that the real part of the complex permeability (μ') is 50 or more at 1 GHz.

10. (Original) The granular substance according to claim 8 or 9, characterized in that the quality factor Q ($Q = \mu' / \mu''$ where μ'' is the imaginary part of the complex permeability) is 5 or more.

11. (Original) The granular substance according to claim 8 or 9, characterized in that the saturation magnetization is 6 kG or more.

12. (Original) The granular substance according to claim 1, characterized in that the resistivity is 100 $\mu\Omega\text{cm}$ or more.

13 – 16 (Cancelled)

17. (Currently Amended) A magnetic device having a magnetic thin film for high frequency,

characterized in that said magnetic thin film for high frequency is formed of a granular substance comprising consisting of:

a ~~matrix composed of a~~ nonmagnetic insulating organic material; and
ferromagnetic metal particles dispersed in said ~~matrix~~ nonmagnetic insulating organic material and having a mean particle size of 50 nm or less,

wherein the volume ratio of said ~~matrix~~ nonmagnetic insulating organic material in said granular substance is in the range of 5 to 50%.

18. (Original) The magnetic device according to claim 17, characterized in that the mean particle size of said ferromagnetic metal particles is in the range of 5 to 30 nm.

19. (Original) The magnetic device according to claim 17, characterized in that said ferromagnetic metal particles are formed of a metal mainly comprising Fe and Co.

20. (Currently Amended) The magnetic device according to claim 17, characterized in that said ~~matrix~~ nonmagnetic insulating organic material is formed of an organic polymer.

21. (Original) The magnetic device according to claim 20, characterized in that:
said organic polymer is a fluorocarbon polymer; and
the resistivity of said magnetic thin film for high frequency is 300 $\mu\Omega\text{cm}$ or more.

22. (Original) The magnetic device according to claim 17, characterized in that said magnetic thin film for high frequency has a complex permeability the real part (μ') of which is 40 or more at 1 GHz, a quality factor Q ($Q = \mu'/\mu''$ where μ'' is the imaginary part of the complex permeability) of 1 or more, and a saturation magnetization of 5 kG or more.